

OSCURANTE

- Smooth dimout fabric with a pleasing haptic and colour matched reverse for a uniform appearance inside and out
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 72°
- Proven acoustic properties

APPLICATIONS



FABRIC PROPERTIES

| | |
|---|----------------------|
|  | Dimout |
|  | Polyester |
|  | 250 g/m ² |
|  | 0.45 mm |
|  | 295 cm |
|  | 300 cm |

FEATURES / TECHNICAL PROPERTIES

| | |
|---|----------------------------|
|  | 5-6 |
|  | Alpha-w = 0.60 |
|  | Flame retardant |
|  | Applicable in humid areas |
|  | Suitable for Wave |
|  | Oeko-Tex |
|  | Special colours from 200 m |

WASHING INSTRUCTIONS



FLAME RETARDANT

Class 1 (EN 13773)
 Class 1 (UNI 8456)
 Type B (BS 5867-2)



Oscurante
OPTICAL AND SOLAR COEFFICIENTS ($\pm 5\%$, DIN EN 410)

| Colour | T_V | T_S | R_S | A_S | F_C | g_{tot} |
|------------|-------|-------|-------|-------|-------|-----------|
| 328 | 0.2 | 0.3 | 56.8 | 42.9 | 0.56 | 0.40 |
| 331 | 0.0 | 0.2 | 45.4 | 54.4 | 0.63 | 0.45 |
| 334 | 0.1 | 0.2 | 54.1 | 45.7 | 0.57 | 0.41 |
| 337 | 0.0 | 0.3 | 31.5 | 68.2 | 0.72 | 0.52 |
| 338 | 0.0 | 0.2 | 28.1 | 71.7 | 0.74 | 0.53 |
| 339 | 0.0 | 0.2 | 33.1 | 66.7 | 0.71 | 0.51 |
| 340 | 0.0 | 0.2 | 40.5 | 59.3 | 0.61 | 0.48 |
| 343 | 0.0 | 0.2 | 32.3 | 67.5 | 0.71 | 0.51 |
| 344 | 0.0 | 0.2 | 31.6 | 68.2 | 0.72 | 0.52 |
| 752 | 0.0 | 0.2 | 41.9 | 57.9 | 0.65 | 0.47 |
| 756 | 0.0 | 0.2 | 47.7 | 52.1 | 0.62 | 0.44 |
| 757 | 0.0 | 0.2 | 37.4 | 62.4 | 0.68 | 0.49 |

T_V Visible light transmission

R_S Solar reflectance

F_C Shading factor

T_S Solar transmission

A_S Solar absorption

g_{tot} Total g-value

$F_C + g_{tot}$: Value calculated with glass: $0.72 / U_g = 1.6 \text{ W/m}^2 \text{ K}$, DIN EN 13363-1

Oscurante

328



331



334



337



338




339



340



343



344



752



756



757

Colours shown are not binding